



LONE MAGNOLIA TECHNOLOGY™
 Enviromental Protection Products

Strom Smith
 1 (832) 330-7078
 Michael Smith
 1 (832) 330-8675

Skinpro Polyurea

Two-Component 100% Solids Polyurea

CHEMICAL RESISTANCE CHART

72 Hour Immersion Test ASTM D3912

Chemical Name	Results @ 25°C
Acetic Acid	R
Acetone	NR
Ammonium Hydroxide (14%)	R
Brake Fluid	R
Brine-Saturated Water (310g/l)	R
Clorox (10%) Water	R
Diesel Fuel	R
Gasoline	R
Gasoline 5% MTBE	R
Gasoline 5% Methanol	R
Hydrochloric Acid (25%)	R
Hydrochloric Acid (10%)	R
Hydraulic Fluid	R
Isopropyl Alcohol	R
Lactic Acid	R
MEK	R
Methanol	R
Methylene Chloride	C
Mineral Spirits	R
Motor Oil	R
MTBE	C
Muriatic Acid (10%)	R
NaCl Water (10%)	R
Nitric Acid (20%)	RC
Phosphoric Acid (10%)	R
Phosphoric Acid (50%)	R
Potassium Hydroxide (10%)	R
Potassium Hydroxide (20%)	R. Dis
Skydrol	R
Sodium Hydroxide (25%)	R. Dis
Sodium Hypochlorite (10%)	R
Sodium Bicarbonate	R
Stearic Acid	R
Sugar Water	R
Sulfuric Acid (10%)	R
Sulfuric Acid (30%)	R
Toluene	RC
Trisodium Phosphate	R
Vinegar Water (5%)	R
Water	R
Water (14 days @ 82°C)	R
Xylene	RC

72 Hour Spot Test Chemical Resistance Data	
Skinpro	
Chemical	Rating
HCL 37.5%	9
NaOH 50%	8
H ₂ SO ₄ 50%	8
HI 57%	8
H ₃ PO ₄ 50%	8
Caustic	8
Brake Fluid	10
Anti-Freeze	10
Motor Oil	10

Rating Guidelines	
0-1	75-100% Film Dissolved
1-2	50-75% Film Dissolved
2-3	25-50% Film Dissolved
3-4	1-25% Film Dissolved
4-5	Film damage severe, cracking, pinholes
5-6	Film moderate to heavy damage, swollen, dulled
6-7	Film moderately damaged, haze, residue
7-8	Film with slight or no damage, slight haze, residue
8-9	Film in very good condition
10	Film unchanged, excellent condition

CHART KEY

- R – Recommended (little or no visible damage)
- RC – Recommended Condition (swelling or discoloration)
- C- Conditional (crackling – wash down within 1 hour)
- NR – Not Recommended
- Dis. – Discoloration